SYNTHESIS, CRYSTAL STRUCURE AND TOTAL CONDUCTIVITY OF La_{2-x}Ba_xNiO_{4±δ}

Jaweed Z., Gilev A.R., Kiselev E.A., Cherepanov V.A. Ural Federal University 620002, Yekaterinburg, Mira str., 19

The Ruddlesden-Popper-type oxides $La_{2-x}Ba_xNiO_{4\pm\delta}$ are considered to be prospective candidates to be used as cathode materials in Solid Oxide Fuel Cells (SOFCs) due to their relatively high mixed ionic and electronic conductivity (MIEC) [1-3]. The replacement of La^{3+} by Ba^{2+} causes extensive changes to the crystal structure, electronic transport behavior, and oxygen diffusivity [1].

In the current study the $La_{2-x}Ba_xNiO_{4\pm\delta}$ samples were prepared using a citratenitrate method followed by solid-state reaction at high temperature (1000-1100 °C). Phase purity was studied by using X-ray diffraction (XRD).

Phase identification analysis reveals that the $La_{2-x}Ba_xNiO_{4\pm\delta}$ samples with x=0.2, 0.6, 0.8, 0.9 1.0 and 1.2 have the tetragonal K₂NiF₄-type structure (space group I4/mmm), whereas for x = 1.4 the formation of secondary phases such as BaNiO₃ or La₆Ba₆Ni₄O₁₈ was observed.

The temperature dependences of total conductivity and the Seebeck coefficient for $La_{2-x}Ba_xNiO_{4\pm\delta}$ (x = 0.2, 0.6) were measured in the range of 25-950 °C. The $La_{1,4}Ba_{0.6}NiO_{4\pm\delta}$ shows the highest electrical conductivity of 40.9 S/cm at 950 °C in air.

Electrical conductivity measurements confirm that charge transport follows a small polaron hopping mechanism, with enhanced conductivity at moderate temperatures and doping levels (x = 0.2-0.6) due to increased Ni³⁺ concentration and electron hole mobility with temperature. At high temperatures excessive oxygen vacancies cause a decrease in Ni³⁺ concentration reducing total conductivity.

1. Niemczyk A., Olszewska A., Du Z., Zhang Z., Świerczek K. and Zhao H. Assessment of layered $La_{2-x}(Sr,Ba)_xCuO_{4-\delta}$ oxides as potential cathode materials for SOFCs. // Int. J. Hydrogen Energy. 2018. V. 43, N. 32, P. 15492–15504.

2. Tang, J.P., Dass, R.I., Manthiram, A. Comparison of the Crystal Chemistry and Electrical Properties of $La_{2-x}A_xNiO_4$ (A = Ca, Sr, Ba). Materials Research Bulletin 2000. V. 35. P. 411-424.

3. Niemczyk, A., Merkle, R., Maier, J., Świerczek, K. Defect chemistry and proton uptake of $La_{2-x}Sr_xNiO_{4\pm\delta}$ and $La_{2-x}Ba_xNiO_{4\pm\delta}$ Ruddlesden-Popper phases. // J. Solid State Chem. 2021. V. 306. P. 122731.

The study was financially supported by the Ministry of Science and Higher Education of Russian Federation [project registration No 123031300049-8].